

Description:

Crona Acian Skimcoat is a product made from selected cement, calcium, and polymer materials that can be used to smooth out uneven or wavy precast concrete surfaces. After application and drying, Crona Acian Skimcoat provides a strong adhesion on the concrete surface, preventing cracks and creating a smooth and non-powdery surface. It is easy to use, lightweight, and has a relatively long application time even in hot weather.

Advantages:

- Easy, lightweight, and fast application
- No cracks or hairline cracks after drying
- Hard and non-powdery surface
- Can be directly painted after drying
- No need for additional wall putty
- Wallpaper can be applied directly after drying

Area of Application:

- Precast Concrete
- Concrete Surfaces (Profiles, Walls, Ceilings)
- Concrete Wall Profiles/Decorations
- Suitable for Internal and External Applications

Substrate Preparation:

- The surface/substrate must be free from dust, oil, and other dirt.
- Uneven surfaces should be made level first.
- Porous and hot surfaces should be conditioned/moistened with clean water before applying the skimcoat.



Product Specification:

- Main Ingredients: Binder made from Cement and Polymer Additives
- Color: Ivory White (with an option for Gray)
- Mixing Ratio: 1 part water to 2.5 – 3 parts powder, or approximately 30 – 32% water of the total dry powder.
- Coverage Rate per m²:
 - 1.25 – 1.3 kg/mm thickness or
 - 30 m²/40 kg for a 1 mm thickness or
 - 15 m²/40 kg for a 2 mm thickness.
 - On average, 12 - 13 m²/40 kg for a 2 – 3 mm thickness.
- Maximum Thickness: 2 mm for a single coating
- Final Thickness: 4 mm for two coatings
- Product Shelf Life: 8 – 12 months in a dry place
- Pot Life: 60 minutes

How-To Application:

- Mix 1 liter of clean water in a prepared container. Then, slowly add 2.5 - 3 kg of Crona Skimcoat product until fully used. For larger scales, the ratio is: 1 part water to 2.5 parts skimcoat powder.
- Stir slowly until it becomes even and homogeneous, with no lumps remaining.
- Let the mixture rest for about 5 minutes, then stir again. The mixture is now ready for application.
- Spread the ready Crona Skimcoat mixture using a flat and flexible trowel while pressing and smoothing it. The maximum thickness for each application is 2 mm. Apply the second coat after the first coat has dried.


Storage & Shelf Life:

Crona Skimcoat product can be stored for 12 months in a dry, well-ventilated place, provided the packaging remains unopened or undamaged.

HEAD OFFICE

Jl. Raya Kelapa Nias GN 11-12
Kel. Kelapa Gading Barat, Kec. Kelapa Gading
Jakarta Utara 14240
Telp. (021) 2245 9009 Fax. (021) 2245 7985
www.mrsafetygroup.com

Mr. SAFETY®
your reliable building partner



BRANCH OFFICE

Ruko Rungkut Makmur Blok D55
Jl. Raya Kali Rungkut No. 27
Surabaya 60293
Telp: (031) 878 3761, 878 3762
Fax: (031) 878 3763